

Material

88 NBR 99035

black

revision index
4

revision date
3/10/2016

page 1 / 2

Physical properties

| | nominal range | typical values | |
|---|----------------|----------------|-------------------|
| Density DIN EN ISO 1183-1 | 1.40 ±0.02 | 1.40 | g/cm ³ |
| Hardness DIN ISO 7619-1 | 88 ±5 | 88 | Shore |
| Tensile strength DIN 53504, S2 | > 15 | 20.9 | MPa |
| Elongation at break DIN 53504, S2 | > 150 | 169 | % |
| Compression set DIN ISO 815, 70 h, 100 °C | --- | 43 | % |
| Temperature range | -25°C to 100°C | | |

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

| | Country | Part | Remark | Expires |
|-------------------|---------|------|---|---------|
| Info ROHS and ELV | | | EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) | see DoC |

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material

88 NBR 99035

black

revision index

4

revision date

3/10/2016

page 2 / 2

No ASTM D2000 properties available

Temperature - range: from -25 °C to 100°C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com