

Material

90 NBR NB902803

Revision Index
05

Revision Date
22.08.2023

General Data

Colour: black
 Type of cross-linking: Sulfur

Physical Properties

	Nominal Range	Typical Value	
Density ASTM D297	1.29 ±0.02	1.29	g/cm ³
Hardness ASTM D2240, Shore A	90 ±5	86	Shore
Tensile strength ASTM D412	>10	19.7	MPa
Elongation at break ASTM D412	>100	206	%
Modulus 100 %, ASTM D412		9.9	MPa
Compression set ASTM D395, Prüfkörper B, 22 h, 100 °C, solid button	25	6	%
Compression set ASTM D395, Prüfkörper B, 22 h, 100 °C, plied sheet	25	13	%

Temperature Range

static: -30 to 100 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025