

Material

93 AU HU2093

Revision Index
01

Revision Date
25.02.2022

General Data

Colour: black

Physical Properties

	Nominal Range	Typical Value
--	---------------	---------------

Hardness ASTM D2240, Shore A, 23 °C	93	Shore
--------------------------------------------	----	-------

Tensile strength ASTM D412	51.7	MPa
-----------------------------------	------	-----

Elongation at break ASTM D412	500	%
--------------------------------------	-----	---

Low temperature resistance ASTM D746, Brittleness	-40	°C
----------------------------------------------------------	-----	----

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025