

Material

93 AU V167

red

revision index
11

revision date
3/30/2022

page 1 / 3

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	1.21 ±0.02	1.21	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	94 ±3	93	Shore
Hardness DIN ISO 7619-1, Shore D, 23 °C	48 ±5	47	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	> 12	13.5	MPa
Tensile strength DIN 53504, S2, 23 °C	> 45	50	MPa
Elongation at break DIN 53504, S2, 23 °C	> 320	397	%
Tear strength DIN ISO 34-1, B (b), 23 °C	---	110	KN/m
Compression set DIN ISO 815, 24 h, 70 °C, 20 %	---	27	%
Compression set DIN ISO 815, 24 h, 100 °C, 20 %	---	34	%
Low Temperature ISO 11357-2, DSC	---	-23	°C
Temperature range	-20°C to 110°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 10/2011	EU		food	see DoC
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
ADI Free			see certificate	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material
93 AU V167
red

revision index
11

revision date
3/30/2022

page 2 / 3

Country Part

Remark
EU2015/863 (ROHS III)

Expires

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material

93 AU V167

red

revision index

11

revision date

3/30/2022

page

3 / 3

No ASTM D2000 properties available

The material fulfills the requirements of FDA.

The operational conditions are defined according "Food Types & Conditions of use for Food Contact Substance" §176.170 Table 2 from B to H of FDA.

The material is suitable for repeated use in all dry, aqueous and acidic foods, except alcoholic foods.

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

