

Technical data sheet in accordance with ASTM

Material

95 AU U958BBK

black

cross linking: peroxidic

revision index

1

revision date

8/6/2021

page

1 / 3

Physical properties

nominal range

typical values

Density

ASTM D297, 23 °C

1.18 ±0.02

1.18

g/cm³

Hardness

ASTM D2240, Shore A, 23 °C

95 ±5

95

Shore

Tensile strength

ASTM D412, C, 23 °C

> 10

54.2

MPa

Elongation at break

ASTM D412, C, 23 °C

> 100

511

%

Temperature range

-40°C to 100°C

Declarations of conformity

No data found!

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

95 AU U958BBK

black

cross linking: peroxidic

revision index

1

revision date

8/6/2021

page

2 / 3

Tested after ASTM D 2000: M 7 BG 910 EA14 EF11 EF21 EO14 EO34 Z1 Z2

		nominal range	typical values
Hardness	Shore	90 ±5	95
Tensile strength	MPa	min. 10	54.2
Elongation at break	%	min. 100	511
A14 Change after aging in Air 70h/100°C			
Hardness	Shore A	---	1
Tensile strength	%	---	2
Elongation at break	%	---	-3
B34 Compression set 22h/100°C			
	%	---	43
EA14 Change after aging in Distilled water 70h/100°C			
Hardness	Shore A	±10	0
Volume	%	±15	2
EF11 Change after aging in Fuel A 70h/23°C			
Hardness	Shore A	±10	0
Tensile strength	%	-25	0
Elongation at break	%	-25	-6
Volume	%	-5 to 10	2
EF21 Change after aging in Fuel B 70h/23°C			
Hardness	Shore A	0 to -30	-2
Tensile strength	%	-60	-30
Elongation at break	%	-60	-7
Volume	%	0 to 40	14
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore A	±5	0

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Technical data sheet in accordance with ASTM

Material

95 AU U958BBK

black

cross linking: peroxidic

revision index	revision date		page	3 / 3	
1	8/6/2021				
		Tensile strength	%	-25	5
		Elongation at break	%	-45	-1
		Volume	%	-10 to 5	0
EO34 Change after aging in IRM 903 70h/100°C					
		Hardness	Shore A	-10 to 5	-1
		Tensile strength	%	-45	4
		Elongation at break	%	-45	-4
		Volume	%	0 to 25	-6
Z1	Modulus 100 %	MPa	---		11.6
Z2	Specific Gravity D1817	g/cc	---		1.18

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com