

Material

98 AU 928

 Revision Index
 06

 Revision Date
 30.03.2022

General Data

Physical Properties

	Nominal Range	Typical Value	
Density DIN EN ISO 1183-1, 23 °C	1.19 ±0.02	1.19	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	97 ±3	97	Shore
Hardness DIN ISO 7619-1, Shore D, 23 °C	55 ±4	55	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	>18	20.8	MPa
Modulus 300 %, DIN 53504, S2, 23 °C		31	MPa
Tensile strength DIN 53504, S2, 23 °C	>48	57	MPa
Elongation at break DIN 53504, S2, 23 °C	>350	456	%
Tear strength DIN ISO 34-1, B (b), 23 °C		155	KN/m
Compression set DIN ISO 815, 24 h, 100 °C, 20 %		35	%
Compression set DIN ISO 815, 70 h, 100 °C, 10 %		39	%
Compression set DIN ISO 815, 24 h, 125 °C, 10 %		55	%
Glass transition temperature ISO 11357-2, DSC		-39	°C
Torsions pendulum test DIN EN ISO 6721-2A		-17	

Temperature Range

static: -30 to 110 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025