

Technical data sheet in accordance with ASTM

# Material

## EPDM EP707103

black

cross linking: sulfur

**revision index**  
2

**revision date**  
11/4/2022

**page** 1 / 2

### Physical properties

	nominal range	typical values	
<b>Density</b> ASTM D 1817	1.10 ±0.03	1.10	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D 2240, Shore A	70 ±5	70	Shore
<b>Tensile strength</b> ASTM D 412	> 10	18.7	MPa
<b>Elongation at break</b> ASTM D 412	> 250	499	%
<b>Low temperature test</b> ASTM D 1329, TR10	< -30	-32	°C
<b>Compression set</b> ASTM D 395, Slab B, 22 h, 100 °C	< 25	21	%
<b>Compression set</b> ASTM D 395, Slab B, 22 h, 125 °C	< 45	40	%
<b>Temperature range</b>	-40°C to 130°C		

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
ADI Free			see certificate	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC
PFOA / PFOS free			see certificate	see DoC

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner

Telefon: -  
 Fax: -  
 Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

## **Material**

### **EPDM EP707103**

black

cross linking: sulfur

**revision index**

2

**revision date**

11/4/2022

**page** 2 / 2

### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner

Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com

