

Technical data sheet in accordance with ASTM

# Material

## EPDM EP801801

violet

cross linking: peroxidic

revision index	revision date	page	1 / 3
2	9/9/2022		
Physical properties	nominal range	typical values	
<b>Density</b> CNS 5341-96	1.36 ±0.03	1.34	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D 2240, Shore A	80 ±5	81	Shore
<b>Modulus</b> 100 %, ASTM D412-16	---	7.1	MPa
<b>Tensile strength</b> ASTM D 412-16	---	14.3	MPa
<b>Elongation at break</b> ASTM D 412-16	---	210	%
<b>Tear strength</b> ASTM D624, B	---	34.3	KN/m
<b>Low Temperature resistance</b> DIN ISO 812, Brittleness	---	-55	°C
<b>Ozone Resistance</b> ASTM D 1171-18, 40 °C, 70 h, 50 pphm	---	0	Rating
<b>Compression set</b> ASTM D 395, Slab B, 22 h, 125 °C	---	12	%
<b>Temperature range</b>	-40°C to 150°C		

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

Country	Part	Remark	Expires
ADI Free		see certificate	see DoC
Info ROHS and ELV		EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner

Telefon: -  
 Fax: -  
 Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

# Material

## EPDM EP801801

violet

cross linking: peroxidic

**revision index**

2

**revision date**

9/9/2022

**page** 2 / 3

### Change after aging in Air: 70h/125°C

Hardness (ASTM D865-11, Shore A)  
Tensile strength (ASTM D865-11)  
Elongation at break (ASTM D865-11)  
weight change

Shore  
MPa  
%  
%

Typ. values			
Base value	After aging	difference	
81	81	0	
14.3	14.4	1 %	
210	216.3	3 %	
	0		

### Change after aging in Water: 70h/100°C

Hardness (ASTM D471, Shore A)  
Tensile strength (ASTM D471)  
Elongation at break (ASTM D471)  
volume change (ASTM D471)

Shore  
MPa  
%  
%

Typ. values			
Base value	After aging	difference	
81	80	-1	
14.3	13.3	-7 %	
210	228.9	9 %	
	1.4		

## Freudenberg

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner

Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

## **Material**

### **EPDM EP801801**

violet

cross linking: peroxidic

**revision index**

2

**revision date**

9/9/2022

**page** 3 / 3

### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner

Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com

