



Technical data sheet in accordance with ASTM

Material FKM FP703401

cross linking: bisphenolically

revision index 1	revision date 7/3/2017		pa	ge 1/2
Physical properties		nominal range	typical values	
Density ASTM D 1817		2.02 ±0.03	2.02	g/cm³
Hardness ASTM D 2240, Shore A		70 ±5	70	Shore
Tensile strength ASTM D 412			14.4	MPa
Elongation at break ASTM D 412			240	%
Tear strength ASTM D 624 C			38	KN/m
Compression set ASTM D 395 B, 22 h, 100 °C,	10 %		10	%

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

Country Info ROHS and ELV	Part	Remark EU 2000/53 (ELV) including EU EU2015/863 (ROHS III)	2011/65		e DoC
Change after aging in Air: 70h/250°C			Base value	Typ. valu After aging	es difference
Hardness (ASTM D2240, Shore A) Tensile strength (ASTM D412) Elongation at break (ASTM D412) volume change (ASTM D471)		Shore MPa %	70 14.4 240	72 15.7 196.8 -3	2 9 % -18 %

Freudenberg

Freudenberg Industrial Services GmbH Global Material Technology Nadja Güldner Telefon: -Fax: -Email: FIS.Compound.CRC@fst.com





Technical data sheet in accordance with ASTM

Material FKM FP703401

cross linking: bisphenolically

revision index

revision date 7/3/2017

page 2/2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH Global Material Technology Nadja Güldner Telefon: -Fax: -Email: FIS.Compound.CRC@fst.com