

Material

FKM FP759412

black

cross linking: peroxidic

revision index
2

revision date
11/9/2022

page 1 / 5

Physical properties

	nominal range	typical values	
Density ASTM D297	2.10 ±0.03	2.09	g/cm ³
Hardness ASTM D2240, Shore A	75 ±5	77	Shore
Tensile strength ASTM D412	---	22.4	MPa
Elongation at break ASTM D412	---	245	%
Low temperature test ASTM D1329, TR10	---	-15	°C
Low Temperature ISO 11357-2, DSC	---	-16.5	°C
Low-temperature resistance ASTM D 2137, 3 min	---	-20	
Ozone Resistance ISO 1431-1 A, 23 °C, 72 h, 50 pphm	---	0	Rating
Compression set ISO 815-1 A, 24 h, 200 °C, 40 %	---	20	%
Compression set ISO 815-1 B, 22 h, 150 °C	---	33	%
Temperature range	-30°C to 210°C short term: 230°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
ADI Free			see certificate	see DoC
BPA/Phthalate free			BPA/Phthalate free	see DoC
FDA	USA	Seals	§ 177.2600	see DoC

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner

Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com



Material

FKM FP759412

black

cross linking: peroxidic

revision index

2

revision date

11/9/2022

page 2 / 5

Country Part

Info ROHS and ELV

Remark

EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) see DoC

Expires

Change after aging

in Air: 72h/250°C

Hardness (ASTM D573, Shore A)
 Tensile strength (ASTM D573)
 Elongation at break (ASTM D573)

Shore
 MPa
 %

Typ. values			
Base value	After aging	difference	
77	76	-1	
22.4	19.9	-11 %	
245	240	-2 %	

Change after aging

in ASTM service fluid # 101: 70h/200°C

Hardness (ASTM D471, Shore A)
 Tensile strength (ASTM D471)
 Elongation at break (ASTM D471)
 volume change (ASTM D471)

Shore
 MPa
 %
 %

Typ. values			
Base value	After aging	difference	
77	81	4	
22.4	17.9	-20 %	
245	205.8	-16 %	
	12		

Change after aging

in ASTM-Oil No. 3: 70h/150°C

Hardness (ASTM D471, Shore A)
 volume change (ASTM D471)

Shore
 %

Typ. values			
Base value	After aging	difference	
77	76	-1	
	1.8		

Change after aging

in FAM A: 72h/23°C

Hardness (ISO 1817, Shore A)
 Tensile strength (ISO 188)
 Elongation at break (ISO 188)
 volume change (ISO 1817)

Shore
 MPa
 %
 %

Typ. values			
Base value	After aging	difference	
77	73	-4	
22.4		%	
245		%	
	2.9		

Change after aging

in FAM B: 72h/23°C

Hardness (ISO 1817, Shore A)
 Tensile strength (ISO 188)
 Elongation at break (ISO 188)
 volume change (ISO 1817)

Shore
 MPa
 %
 %

Typ. values			
Base value	After aging	difference	
77	67	-10	
22.4		%	
245		%	
	13		

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner

Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com



Material

FKM FP759412

black

cross linking: peroxidic

revision index
2

revision date
11/9/2022

page 3 / 5

Change after aging in Fluid F: 72h/23°C

Hardness (ISO 1817, Shore A)
Tensile strength (ISO 188)
Elongation at break (ISO 188)
volume change (ISO 1817)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
77	76	-1	
22.4			%
245			%
	0.3		

Change after aging in Fuel C: 70h/23°C

Hardness (ASTM D471, Shore A)
Tensile strength (ASTM D471)
Elongation at break (ASTM D471)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
77	74	-3	
22.4	19	-15	%
245	220.5	-10	%
	4		

Change after aging in IRM 903: 168h/150°C

Hardness (ASTM D471, Shore A)
Tensile strength (ASTM D471)
Elongation at break (ASTM D471)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
77	74	-3	
22.4	21.3	-5	%
245	250	2	%
	1.9		

Change after aging in Steam: 70h/140°C

Hardness (ISO 1817, Shore A)
Tensile strength (ISO 1817)
Elongation at break (ISO 1817)
volume change (ISO 1817)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
77	74	-3	
22.4	20.6	-8	%
245	255	4	%
	3.6		

Change after aging in Steam: 168h/150°C

Hardness (ASTM D471, Shore A)
volume change (ASTM D471)

Shore
%

Typ. values			
Base value	After aging	difference	
77	73	-4	
	4		

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com



Material

FKM FP759412

black

cross linking: peroxidic

revision index

2

revision date

11/9/2022

page 4 / 5

Change after aging in Water: 70h/140°C

Hardness (ISO 1817, Shore A)
Tensile strength (ISO 1817)
Elongation at break (ISO 1817)
volume change (ISO 1817)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
77	73	-4	
22.4	19.7	-12 %	
245	257	5 %	
	4.3		

Change after aging in Water: 70h/200°C

Hardness (ASTM D471, Shore A)
Tensile strength (ASTM D471)
Elongation at break (ASTM D471)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
77	81	4	
22.4	19	-15 %	
245	196	-20 %	
	8		

Lagerung nach ASTM D 471 und ASTM D 573

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com



Material

FKM FP759412

black

cross linking: peroxidic

revision index

2

revision date

11/9/2022

page 5 / 5

No ASTM D2000 properties available

Compliant with the EU-directives 2000/53/EC (ELV).

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com

