

Technical data sheet in accordance with ASTM

# Material

## FKM FP801804

green

cross linking: bisphenolically

**revision index**  
3

**revision date**  
2/5/2024

**page** 1 / 3

### Physical properties

	nominal range	typical values	
<b>Density</b> CNS 5341-96	2.12 ±0.03	2.11	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240-15, Shore A	80 ±5	79	Shore
<b>Tensile strength</b> ASTM D412-16	---	16.8	MPa
<b>Elongation at break</b> ASTM D412-16	---	179	%
<b>Modulus</b> 100 %, ASTM D412-16	---	9.5	MPa
<b>Compression set</b> ASTM D395-18, Slab B, 22 h, 175 °C, plied	---	11	%
<b>Compression set</b> ASTM D395-18, Slab B, 22 h, 200 °C, plied	---	15	%
<b>Low temperature test</b> ASTM D1329-16, TR10	---	-16.3	°C

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
ADI Free			see certificate	see DoC
DVGW Baumusterprüfzertifikat Gas	D		DIN EN 549 H3 E1	11 / 2026
DVGW type examination certificate gas	D		DIN EN 549 H3 E1	11 / 2026
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner

Telefon: -  
 Fax: -  
 Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

# Material

## FKM FP801804

green

cross linking: bisphenolically

**revision index**

3

**revision date**

2/5/2024

**page** 2 / 3

### Change after aging in Air: 70h/250°C

Hardness (ASTM D573-04, Shore A)  
Tensile strength (ASTM D573-04)  
Elongation at break (ASTM D573-04)  
weight change

Shore  
MPa  
%  
%

Typ. values			
Base value	After aging	difference	
79	80	1	
16.8	13.8	-18 %	
179	180.8	1 %	
	-2.5		

### Change after aging in ASTM service fluid # 101: 70h/200°C

Hardness (ASTM D471-16a, Shore A)  
Tensile strength (ASTM D471-16a)  
Elongation at break (ASTM D471-16a)  
volume change (ASTM D471-16a)

Shore  
MPa  
%  
%

Typ. values			
Base value	After aging	difference	
79	69	-10	
16.8	12.6	-25 %	
179	173.6	-3 %	
	11.2		

### Change after aging in Fuel C: 70h/23°C

Hardness (ASTM D471-16a, Shore A)  
Tensile strength (ASTM D471-16a)  
Elongation at break (ASTM D471-16a)  
volume change (ASTM D471-16a)

Shore  
MPa  
%  
%

Typ. values			
Base value	After aging	difference	
79	76	-3	
16.8	14.6	-13 %	
179	164.6	-8 %	
	4.6		

## Freudenberg

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner

Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com



Technical data sheet in accordance with ASTM

## **Material**

### **FKM FP801804**

green

cross linking: bisphenolically

**revision index**

3

**revision date**

2/5/2024

**page** 3 / 3

### **No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner

Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com

