

Material

NBR MT0479

polyamide fabric + elastomeric rubber

Revision Index
02

Revision Date
28.02.2022

General Data

Colour: blue

Physical Properties

	Nominal Range	Typical Value
Thickness DIN EN ISO 2286-3	0.17 ±0.03	mm
Width DIN EN ISO 2286-1	1400 ±100	mm
Grammage DIN EN ISO 2286-2	210 ±40	
Tensile strength DIN EN ISO 1421,Verfahren 1,längs Kette/warp	>550	MPa
Tensile strength DIN EN ISO 1421,Verfahren 1,quer Schuß/weft	>650	MPa
Elongation at break DIN EN ISO 1421,Verfahren 1,längs Kette/warp	>20	%
Elongation at break DIN EN ISO 1421,Verfahren 1,quer Schuß/weft	>30	%
Bursting pressure DIN EN ISO 13938-1, 50 cm ²	>4	bar
swelling, weight gain DIN ISO 1817, Isooctan/Toluol (70:30), 24 h, 23 °C, einseitig	<5	%
swelling, weight gain DIN ISO 1817, IRM 902, 72 h, 100 °C, all-sided	<6	%

Temperature Range

static: -25 to 90 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 30.04.2025