

Technical data sheet in accordance with ASTM

Material

NBR NB603410

black

cross linking: sulfur

revision index

2

revision date

7/3/2017

page

1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D 1817, 23 °C	1.23 ±0.02	1.23	g/cm ³
Hardness ASTM D2240, Shore A, 23 °C	60 ±5	60	Shore
Tensile strength ASTM D412	---	11	MPa
Elongation at break ASTM D412	---	371	%
Low temperature test ASTM D1329, TR10	---	-34.5	°C
Surface resistivity ICE 93, 23 °C	---	4.6e+008	Ohm
Compression set ASTM D395, Slab B, 22 h, 100 °C, 25 %	---	6	%
Ozone Resistance 40 °C, 72 h, 50 pphm, 20% Elongation	---	0	Rating
Low-temperature resistance ASTM D 2137, 3 min, pass	---	-40	
Temperature range	-40°C to 100°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner
 Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

Material

NBR NB603410

black

cross linking: sulfur

revision index
2

revision date
7/3/2017

page 2 / 3

Change after aging in Air: 70h/100°C

Hardness (ASTM D2240, Shore A, 23 °C)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
60	71	11	
11	13.1	19 %	
371	311.6	-16 %	

Change after aging in ASTM-Oil No. 1: 70h/100°C

Hardness (ASTM D2240, Shore A, 23 °C)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
60	67	7	
11	13.2	20 %	
371	296.8	-20 %	
	-7		

Change after aging in IRM 903: 70h/100°C

Hardness (ASTM D2240, Shore A, 23 °C)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
60	63	3	
11	11.9	8 %	
371	293.1	-21 %	
	1		

Change after aging in Water: 70h/100°C

Hardness (ASTM D2240, Shore A, 23 °C)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
60	58	-2	
11	10.9	-1 %	
371	326.5	-12 %	
	3		

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

Material

NBR NB603410

black

cross linking: sulfur

revision index

2

revision date

7/3/2017

page 3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com