

Material

NBR NB702717

black

cross linking: sulfur

revision index

3

revision date

11/22/2018

page

1 / 4

Physical properties

	nominal range	typical values	
Density DIN 53479	1.23 ±0.02	1.23	g/cm ³
Hardness DIN 53505, Shore A	70 ±5	70	Shore
Tensile strength DIN 53504	---	15	MPa
Elongation at break DIN 53504	---	340	%
Compression set DIN 53517, Slab A, 168 h, 100 °C, 25 %	---	31	%
Compression set DIN 53517, Slab A, 72 h, 0 °C, 25 %	---	13	%
Compression set DIN 53517, Slab A, 22 h, 100 °C, 25 %	---	13	%
Compression set DIN 53517, Slab A, 72 h, -20 °C, 25 %	---	44	%
Low-temperature resistance DIN 53546, brittleness point	---	-34	
Low temperature test ASTM D1329, TR10	---	-30	°C
Low temperature test ASTM D1329, TR50	---	-23	°C
Temperature range	-30°C to 100°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
ADI Free DVGW	D		see certificate DIN EN 549 H3 B2	see DoC 07 / 2024

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner

Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com



Material

NBR NB702717

black

cross linking: sulfur

revision index

3

revision date

11/22/2018

page 2 / 4

Country Part

Remark

Expires

Baumusterprüfzertifikat
 Gas
 Info ROHS and ELV

EU 2000/53 (ELV) including EU 2011/65 and see DoC
 EU2015/863 (ROHS III)

Change after aging in Air: 168h/100°C

Typ. values

Base value	After aging	difference
70	77	7
15	16.5	10 %
340	251.6	-26 %

Hardness (DIN 53505, Shore A)
 Tensile strength (DIN 53504)
 Elongation at break (DIN 53504)

Shore
 MPa
 %

Change after aging in Air: 72h/125°C

Typ. values

Base value	After aging	difference
70	79	9
15	15.3	2 %
340	221	-35 %

Hardness (DIN 53505, Shore A)
 Tensile strength (DIN 53504)
 Elongation at break (DIN 53504)

Shore
 MPa
 %

Change after aging in ASTM-Oil No. 1: 72h/100°C

Typ. values

Base value	After aging	difference
70	75	5
15	16.5	10 %
340	261.8	-23 %
	-7	

Hardness (DIN 53505, Shore A)
 Tensile strength (DIN 53504)
 Elongation at break (DIN 53504)
 volume change (DIN 53508)

Shore
 MPa
 %
 %

Change after aging in ASTM-Oil No. 3: 72h/100°C

Typ. values

Base value	After aging	difference
70	64	-6
15	15.8	5 %
340	289	-15 %
	8	

Hardness (DIN 53505, Shore A)
 Tensile strength (DIN 53504)
 Elongation at break (DIN 53504)
 volume change (DIN 53508)

Shore
 MPa
 %
 %

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner

Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com



Material

NBR NB702717

black

cross linking: sulfur

revision index

3

revision date

11/22/2018

page 3 / 4

Change after aging in Water: 70h/100°C

Hardness (DIN 53505, Shore A)
Tensile strength (DIN 53504)
Elongation at break (DIN 53504)
volume change (DIN 53508)

Shore
MPa
%
%

Typ. values

Base value	After aging	difference
70	70	0
15	16.2	8 %
340	292.4	-14 %
	3	

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com



Material NBR NB702717

black

cross linking: sulfur

revision index

3

revision date

11/22/2018

page 4 / 4

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com

