

Technical data sheet in accordance with ASTM

# Material

## NBR NB708403

black

cross linking: sulfur

revision index

1

revision date

3/4/2020

page

1 / 3

### Physical properties

	nominal range	typical values	
<b>Density</b> ASTM D 1817	1.26 ±0.02	1.26	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D 2240, Shore A	70 ±5	72	Shore
<b>Tensile strength</b> ASTM D 412	---	19.2	MPa
<b>Elongation at break</b> ASTM D 412	---	390	%
<b>Compression set</b> ASTM D 395, Slab B, 22 h, 100 °C, 25 %	---	15	%

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

### Change after aging

#### in Air: 70h/100°C

		Typ. values		
		Base value	After aging	difference
Hardness (ASTM D2240, Shore A)	Shore	72	75	3
Tensile strength (ASTM D412)	MPa	19.2	22.1	15 %
Elongation at break (ASTM D412)	%	390	378	-3 %

### Change after aging

#### in ASTM-Oil No. 1: 70h/100°C

		Typ. values		
		Base value	After aging	difference
Hardness (ASTM D2240, Shore A)	Shore	72	75	3
Tensile strength (ASTM D412)	MPa	19.2	22.1	15 %
Elongation at break (ASTM D412)	%	390	370	-5 %
volume change (ASTM D471)	%		-7.8	

### Freudenberg

Freudenberg Industrial Services GmbH  
 Global Material Technology  
 Nadja Güldner  
 Telefon: -  
 Fax: -  
 Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

## Material

### NBR NB708403

black

cross linking: sulfur

**revision index**

1

**revision date**

3/4/2020

**page** 2 / 3

#### Change after aging in IRM 903: 70h/100°C

#### Typ. values

Hardness (ASTM D2240, Shore A)  
Tensile strength (ASTM D412)  
Elongation at break (ASTM D412)  
volume change (ASTM D471)

Shore  
MPa  
%  
%

Base value	After aging	difference
72	67	-5
19.2	19	-1 %
390	355	-9 %
	3.3	

### Freudenberg

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner  
Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

## **Material**

### **NBR NB708403**

black

cross linking: sulfur

**revision index**

1

**revision date**

3/4/2020

**page** 3 / 3

**No ASTM D2000 properties available**

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### **Freudenberg**

Freudenberg Industrial Services GmbH  
Global Material Technology  
Nadja Güldner  
Telefon: -  
Fax: -  
Email: FIS.Compound.CRC@fst.com