

Material PA 4201

revision index
2

revision date
2/6/2024

page 1 / 2

Physical properties

typical values

Density DIN EN ISO 1183-1, 23 °C	116.00	g/cm ³
Elongation at break DIN EN ISO 527, S2, 23 °C	3.5	%
Tensile Stress at Yield DIN EN ISO 527	95	MPa
Tensile modulus DIN EN ISO 527, 23 °C, PR	3500	MPa
Notched impact strength ISO 179/1eA, Charpy	4.7	kJ/m ²
Temperature range	to 90°C	

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance
Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

Material PA 4201

revision index

2

revision date

2/6/2024

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com