

Material PTFE C104

Revision Index Revision Date

05 14.11.2018

General Data

Colour: anthracite

Filler: carbon fibre, %

Physical Properties	Nominal Range	Typical Value	
Density DIN EN ISO 1183-1, 23 °C		2.09	g/cm³
Hardness DIN ISO 7619-1, Shore D, 23 °C, 3 sec.		60	Shore
Ball indentation hardness DIN EN ISO 2039-1, 23 °C		32	MPa
Tensile strength at break on basis of DIN EN ISO 527, SPI, 23 $^{\circ}\text{C},$ UR		22	MPa
Elongation at break on basis of DIN EN ISO 527, SPI, 23 °C		280	%

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025