

# Material

## PTFE G602

Flex-O-Form S®

Revision Index  
05

Revision Date  
27.08.2020

### General Data

Colour: beige

Declaration of Compliance for - Food & Beverage is available upon request for selected articles. Please contact your known sales contact or send an email to [info@fst.com](mailto:info@fst.com).

### Physical Properties

	Nominal Range	Typical Value
<b>Density</b> DIN EN ISO 1183-1, 23 °C		2.17 g/cm³
<b>Hardness</b> DIN ISO 7619-1, Shore D, 23 °C, 3 sec.		57 Shore
<b>Ball indentation hardness</b> DIN EN ISO 2039-1, 23 °C		29 MPa
<b>Tensile strength at break</b> on basis of DIN EN ISO 527, SPI, 23 °C, UR		23 MPa
<b>Elongation at break</b> on basis of DIN EN ISO 527, SPI, 23 °C		380 %

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 29.04.2025