

Material PTFE Y002

Revision Index
06**Revision Date**
21.09.2023**General Data**

Colour: beige

Declaration of Compliance for - Food & Beverage - Pharmaceutical is available upon request for selected articles. Please contact your known sales contact or send an email to info@fst.com.

Physical Properties

	Nominal Range	Typical Value
Density DIN EN ISO 1183-1, 23 °C		2.03 g/cm ³
Hardness DIN ISO 7619-1, Shore D, 23 °C, 3 sec.		59 Shore
Ball indentation hardness DIN EN ISO 2039-1, 23 °C		37 MPa
Tensile strength on basis of DIN EN ISO 527, SPI, 23 °C, UR		24 MPa
Elongation at break on basis of DIN EN ISO 527, SPI, 23 °C		380 %

Temperature Range

static: -80 to 200 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry. The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Print date: 30.04.2025