

Material
PTFE 177028

black

revision index	revision date	page	1 / 2
1	7/22/2021		

Physical properties	nominal range	typical values	
Density DIN EN ISO 1183-1	2.29 ±0.03	---	g/cm ³
Ball indentation hardness DIN EN ISO 2039-1	---	35	MPa
Tensile strength DIN EN ISO 527	---	22	MPa
Elongation at break DIN EN ISO 527	---	300	%
Temperature range	-200°C to 260°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country Part	Remark	Expires
ADI Free		see certificate	see DoC
Conflict Mineral Free		see certificate	see DoC
Info ROHS and ELV		EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC
PFOA / PFOS free		see certificate	see DoC

Freudenberg
Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material PTFE 177028

black

revision index

1

revision date

7/22/2021

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

