

# Material

## PTFE B500

brown

**revision index**

3

**revision date**

11/19/2019

**page**

1 / 2

### Physical properties

**typical  
values**

**Density**

DIN EN ISO 1183-1, 23 °C

3.50

g/cm<sup>3</sup>

**Hardness**

DIN ISO 7619-1, Shore D, 23 °C, 3 sec.

65

Shore

**Tensile strength**

DIN 53455, S2, 23 °C

16

MPa

**Elongation at break**

DIN 53455, S2, 23 °C

200

%

### Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

**Country Part**

**Remark**

**Expires**

Info ROHS and ELV

EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III) see DoC

### Freudenberg

Freudenberg FST GmbH

Technology&Innovation

Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

## Material PTFE B500

brown

**revision index**

3

**revision date**

11/19/2019

**page** 2 / 2

### No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### Freudenberg

Freudenberg FST GmbH  
Technology&Innovation  
Material Compliance

Telefon: -

Fax: -

Email: [MaterialCompliance@fst.com](mailto:MaterialCompliance@fst.com)