

Material

PTFE E202

beige

revision index

3

revision date

11/14/2018

page 1 / 2

Physical properties

Density

DIN EN ISO 1183-1, 23 °C

typical
values

1.93 g/cm³

Hardness

DIN ISO 7619-1, Shore D, 23 °C, 3 sec.

60 Shore

Ball indentation hardness

DIN EN ISO 2039-1, 23 °C

35 MPa

Tensile strength

on basis of DIN EN ISO 527, SPI, 23 °C, UR

16 MPa

Elongation at break

on basis of DIN EN ISO 527, SPI, 23 °C

280 %

Temperature range

to 210°C

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 10/2011	EU		food	see DoC
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
ADI Free				see DoC
Conflict Mineral Free				see DoC
FDA	USA	Seals	§ 177.1550	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material PTFE E202

beige

revision index
3

revision date
11/14/2018

page 2 / 2

No ASTM D2000 properties available

According the BAM "Bundesanstalt für Materialprüfung" (Federal Institute for Material Research) certificate of February 2012, the investigated sample of the material is safe for use in valves for gaseous oxygen if the following operating parameters are not exceeded.

The tests had been carried out with one sample from one lot and deliver only indicative results.

Temp. up to 60°C max. oxygen pressure 30 bar
Temp. >60°C to 90°C max. oxygen pressure 20 bar

The given values are based on a limited number of tests on standard test pieces produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Attention! The production of this compound is suspended. Please contact us.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

