

Material

PTFE F52803

white

revision index
2

revision date
2/1/2018

page 1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	2.18 +0.02/-0.04	2.17	g/cm ³
Hardness DIN ISO 7619-1, Shore D, 23 °C, cylinder diam. 50x50 mm, after 3 s	56 ±2	55	Shore
Tensile strength DIN EN ISO 527-1, FD-105, 23 °C, Cross Direction	27 +8/-7	24.3	MPa
Elongation at break DIN EN ISO 527-1, FD-105, 23 °C, Cross Direction	300 ±100	311	%

Temperature range -200°C to 260°C

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Conflict Mineral Free			see certificate	see DoC
FDA	USA	Seals	§ 177.1550	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material PTFE F52803

white

revision index

2

revision date

2/1/2018

page 2 / 2

No ASTM D2000 properties available

The composition of the material accords to the regulation of the EU-directive EC no. 10/2011.

The given values are based on a limited number of tests on standard test pieces (1,5mm foil) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com