

# Material PTFE K208

black

carbon filled polytetrafluoroethylene

revision index 4	revision date 11/14/2018	page	1/2
Physical properties		typical values	
Density DIN EN ISO 1183-1, 23	°C	2.09	g/cm³
Hardness DIN ISO 7619-1, Shore	D, 23 °C, 3 sec.	65	Shore
Ball indentation hardn DIN EN ISO 2039-1, 23		49	MPa
Tensile strength on basis of DIN EN ISO	527, SPI, 23 °C, UR	19	MPa
Elongation at break on basis of DIN EN ISO	9 527, SPI, 23 °C	190	%

## **Declarations of conformity**

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	<b>Expires</b>
ADI Free			see certificate	see DoC
Conflict Mineral Free			see certificate	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

## Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance

Telefon: -Fax: -

Email: MaterialCompliance@fst.com





## Material PTFE K208

black

carbon filled polytetrafluoroethylene

revision index revision date 4 11/14/2018

page 2/2

#### No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

## Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance

Telefon: -Fax: -

Email: MaterialCompliance@fst.com

