



Technical data sheet in accordance with ASTM

Material PTFE PT009809

black

with carbon + graphite

revision index 2	revision date 2/5/2024		page	1/2
Physical properties		nominal range	typical values	
Density ASTM D 792		2.10 ±0.02	2.10	g/cm³
Hardness ASTM D 2240, Shore D, 23 °C			60	Shore
Tensile strength ASTM D 4894			18.4	MPa
Elongation at break ASTM D 4894			202	%

Temperature range -200°C to 280°C

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
Conflict Mineral Free			see certificate	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC
PFOA / PFOS free			see certificate	see DoC

Freudenberg

Freudenberg Industrial Services GmbH Global Material Technology Nadja Güldner

Telefon: -Fax: -

Email: FIS.Compound.CRC@fst.com





Technical data sheet in accordance with ASTM

Material PTFE PT009809

black

with carbon + graphite

revision index revision date

2 2/5/2024 page 2/2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH Global Material Technology Nadja Güldner

Telefon: -Fax: -

Email: FIS.Compound.CRC@fst.com