

Technical data sheet in accordance with ASTM

Material

PTFE PT00A202

brown

PTFE + bronze

revision index
1

revision date
11/7/2017

page 1 / 2

Physical properties

	nominal range	typical values	
Density ASTM D 792	3.07 ±0.09	3.07	g/cm ³
Hardness ASTM D 2240, Shore D	> 58	---	Shore
Tensile strength ASTM D 4745, Cross Direction	> 18	---	MPa
Elongation at break ASTM D 4745, Cross Direction	> 200	---	%
Compressive Strength ASTM D 695, 1 % Verzug / Compressive strength	> 8	---	MPa
Deformation under load ASTM D 621, 23 °C, 24 h, 13.7 N/mm ² , Cross Direction	< 8	---	%
Deformation under load ASTM D 621, 23 °C, 24 h, ruhend / at rest ; Cross Direction	< 5	---	%

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner
 Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

Material

PTFE PT00A202

brown

PTFE + bronze

revision index

1

revision date

11/7/2017

page 2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com