

Technical data sheet in accordance with ASTM

Material TPC HT2055

orange

revision index 1	revision date 1/31/2022		paç	ge 1/2
Physical properties		nominal range	typical values	
Density ASTM D297, 23 °C			1.22	g/cm³
Hardness ASTM D2240, Shore d, 23 °C			60	Shore
Tensile strength ASTM D638			39.3	MPa
Elongation at break ASTM D412			300	%
Flexural modulus ASTM D790			275.8	MPa

Temperature range -51°C to 149°C

Declarations of conformity No data found!

Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance

Telefon: -Fax: -

Email: MaterialCompliance@fst.com



Technical data sheet in accordance with ASTM

Material TPC HT2055

orange

revision index revision date

1 1/31/2022 page 2/2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance

Telefon: -Fax: -

Email: MaterialCompliance@fst.com