


FREUDENBERG

Radial seal Merkel® Rotomatic M16

DESCRIPTION

- Two-piece
- O-ring as sealing and preloading element

FUNCTION

- For installation spaces in accordance with DIN ISO 7425/1, among others
- Sealing of pistons
- For pressure load from both sides
- Lubricant depot due to circumferential grooves in dynamic sealing surface

PRODUCT ADVANTAGES

- Good media resistance
- Low friction
- Market-leading, proprietary design with the widest range of applications in all industries and for a variety of requirements
- No stick-slip effect
- Highest quality, durability and safety
- Best results in total cost of ownership

APPLICATIONS


- Excavator
- Rotary unions
- Grippers

CONFORMITY AND CERTIFICATES


- Please consult the material data sheet valid for the respective material for current information on approvals and certificates, as this information depends on the compound and cannot be listed exhaustively here.

DESIGN GUIDELINE

- Sharp edges deburred or chamfered or rounded
- To avoid damage, cylinder tubes and piston rods must be chamfered, surface finish Rt=4m
- Please follow the QR code or hyperlink to the technical manual to obtain further information and instructions.



FREUDENBERG
SEALING TECHNOLOGIES



FREUDENBERG

Radial seal Merkel® Rotomatic M16

INSTALLATION GUIDELINE

- No machining residues, chips, dirt, etc.
- Do not pull the seal over sharp edges, threads, or keyways during installation; cover with an installation sleeve if necessary
- Oil or grease the seal, piston rod, and cylinder tube before installation
- Please follow the QR code or hyperlink to the technical manual to obtain further information and instructions.


STORAGE ADVISE

- Storage temperature <25°C
- No direct heat sources
- No direct sunlight
- No condensation in the storage room
- No exposure to ozone or ionizing radiation
- Recommendations based on the revision of ISO 2230 dated 16.09.1992

Pressure [MPa]
40

Sliding speed [m/s]
0.5

FREUDENBERG
SEALING TECHNOLOGIES



FREUDENBERG

Radial seal Merkel® Rotomatic M16

Temperature [°C]

Medium	PTFE GM201 / NBR	PTFE GM201 / FKM
Hydraulic oils HL, HLP	-30...100	-10...150
HFA fluids	5...60	5...60
HFB fluids	5...60	5...60
HFC fluids	-30...60	-10...40
HFD fluids		-10...150
Water	5...100	5...100
HETG (rapeseed oil)	-30...80	-10...80
HEES (synthetic esters)	-30...60	-10...100
HEPG (polyglycols)	-30...60	-10...80
Mineral greases	-30...100	-10...150

The values given are based on a limited number of tests on standard test specimens (2 mm sample plates) from laboratory production. The data determined from finished parts may deviate from the above values depending on the manufacturing process and the part geometry.

The information provided herein is based on laboratory tests and on data sources deemed reliable. It constitutes general, non-binding guideline values and does not represent any guarantee of specific properties or suitability for a particular purpose. The suitability of a product for a specific application depends on the actual operating conditions and a variety of factors. Full testing and performance evaluation of the final product are the responsibility of the user. Freudenberg FST GmbH | www.fst.com

FREUDENBERG
SEALING TECHNOLOGIES