




DICHTOMATIK

Rod seal SPOR30

DESCRIPTION

- Symmetrical
- Double-acting
- O-ring as sealing and preloading element
- Tight fit on the outer diameter

FUNCTION

- Sealing of piston rods
- For pressure load from both sides
- Use as a primary or secondary seal in a sealing system

APPLICATIONS

- Standard cylinders
- Stationary hydraulics

CONFORMITY AND CERTIFICATES


- Please consult the material data sheet valid for the respective material for current information on approvals and certificates, as this information depends on the compound and cannot be listed exhaustively here.

PRODUCT ADVANTAGES

- Low friction even at low speed
- High chemical resistance
- High wear resistance
- Wide temperature range
- High extrusion reliability
- Reliable design with broad application spectrum for moderately demanding applications in general industry
- No stick-slip effect
- Good price/performance ratio
- Manufactured by certified external suppliers
- Suitable for dry running and deficient lubrication

DESIGN GUIDELINE

- Installation space cleaned and free of deposits or old packing rings
- Please refer to the technical manual for design guidelines.
- Surface roughness of the groove flanks $Ra \leq 3 \mu m$
- With pulsating pressures, hardness of the o-ring should not be less than 80 Shore A
- Counterface surface roughness $Ra \leq 2 \mu m$




DICHTOMATIK



DICHTOMATIK

Rod seal SPOR30



INSTALLATION GUIDELINE

- Axially accessible installation space required for small diameters
- Semi-open or closed installation spaces possible for a limited dimensional range
- Deburr sharp edges, provide with seamless chamfers and radii
- Clean the installation space carefully before installation, remove dust, dirt, metal chips, etc.
- Do not pull the seal over sharp edges, threads, or keyways during installation; cover with an installation sleeve if necessary
- When installing in closed installation spaces, heat the PTFE part in advance so that the seal can be installed quickly and easily by forming it into a kidney shape
- The seal must not be kinked during installation
- Do not roll the O-ring over the mounting surfaces, do not twist it when snapping into the groove
- Oil or grease the piston rod before installation
- Calibrate at the end

STORAGE ADVISE


- No direct heat sources
- No direct sunlight
- No condensation in the storage room
- No exposure to ozone or ionizing radiation
- Recommendations based on the revision of ISO 2230 dated 16.09.1992



DICHTOMATIK



FREUDENBERG
SEALING TECHNOLOGIES



Rod seal SPOR30

Pressure [MPa]

PTFE

40

Sliding speed [m/s]

PTFE

15

Temperature [°C]

PTFE

-30...100

The values given are based on a limited number of tests on standard test specimens (2 mm sample plates) from laboratory production. The data determined from finished parts may deviate from the above values depending on the manufacturing process and the part geometry.

The information provided herein is based on laboratory tests and on data sources deemed reliable. It constitutes general, non-binding guideline values and does not represent any guarantee of specific properties or suitability for a particular purpose. The suitability of a product for a specific application depends on the actual operating conditions and a variety of factors. Full testing and performance evaluation of the final product are the responsibility of the user. Freudenberg FST GmbH | www.fst.com

